



Technical Data Sheet (TDS)  
產品理化數據

**Flower Matt Latex Paint 000 Series**

09/12

Description		Standard Method	Result
Preliminary Examination of Paint	Surface Skin	BS 3900 : A2	NO
	Consistency		Normal
	Separation of Phases		NO
	Visible Impurities		NO
Viscosity (Stormer Viscometer)		ASTM D 562	95- 110 KU (25℃)
Specific Gravity		BS 3900 : A12	1.35--1.45
Fineness of Grind (μm)		BS 3900 : C6	≅ 50 μm
Drying Times (25℃, RH70%)	Surface Drying (mins)	BS 3900 : C2	< 1hr
	Hard Drying (hrs)	BS 3900 : C3	< 2hr
Specular Gloss (60°)		BS 3900 : D5	≅ 5%
Opacity(or Hiding Power) (contrast ratio %)		GB/T 9756	≅ 0.95
Wet Scrub Test		GB/T 9266	≅ 2000 cycles pass
Water Resistance		ASTM D 870	48 hours pass
Alkali Resistance		GB/T9756	24 hours pass
No Lead (Pb)		GB18582	≅ 90 ppm