



Technical Data Sheet (TDS)
產品理化數據

Giraffe Brushing Lacquer #2300HK
Technical Specification

Version Date: 2010/1/13

TEST ITEMS		TEST STANDARD	TEST RESULT
Appearance of paint		Observe with eyes	No impurity
Appearance of film		Observe with eyes	Level and smooth
Fineness of Grind		GB/T 1724-1979	$\leq 40\mu\text{m}$
Drying Time	Surface Dry	GB/T 1728-1979(Second law of chapter two)	≤ 10 minutes
	Hard Dry	GB/T 1728-1979(First law of chapter three)	≤ 50 minutes
Finish (3Mil/60°)		WI-科技-T1-012	Various kinds of colors are available on request
Solid Content		GB/T 1725-1979 (First law of chapter two)	$\geq 38\%$
Pencil Hardness		GB/T 6739-1996	$\geq 2\text{B}$
Cross Cut Test, grade		GB/T 9286-1998	≤ 2
VOC, g/l		P08-14	≤ 650

Remark:

GB: Test Standard Of PRC,

WI: Enterprise Test Method Of China Paint