

## Giraffe Clear Furniture Lacquer, Gloss

Update: 15/8/2011

	PRODUC	T SPECIFICA	ATION	
PRODUCT NUMBER	#322HK			
PRODUCT NAME	Giraffe Clear Furn	iture Lacquer, Glo	SS	
INTRODUCTION				
RECOMMENDED USES	For topcoating interior wood surfaces.			
PRODUCT DESCRIPTION	<ul> <li>It is a fast drying and high gloss wood lacquer.</li> <li>High solid content</li> <li>Good film build</li> <li>Good adhesion and yellowing resistance</li> <li>Resistant to water and salt erosion</li> </ul>			
	Free from benzene		v the natural beauty of omethane, ethylene chi	J
	TEC	HNICAL DATA		
VEHICLE	Nitrocellulose			
COLOUR	Clear			
GLOSS	Gloss			
VOLUME SOLIDS	Approx. 40%			
TYPICAL DRY FILM THICKNESS	20-30 microns			
	* Approx. 16 sq. m/ L/ 1 coat (At 25 microns)			
CALCULATED COVERAGE	* Approx. 16 sq. m/	' L/ 1 coat (At 25 m	icrons)	
COVERAGE	* Approx. 16 sq. m/ Touch Dry	' L/ 1 coat (At 25 m Hard Dry	icrons) Overcoating	
			·	
COVERAGE  DRYING TIME AT	Touch Dry	Hard Dry  2 hours  * Based on theoretical	Overcoating Min 30 mins	
COVERAGE  DRYING TIME AT	Touch Dry 10 mins	Hard Dry  2 hours  * Based on theoretical	Overcoating Min 30 mins Max Indefinite consumption; factors such as pair	



THE CHINA PAINT MFG. CO. (1932) LTD.

31/F., CNT Tower, 338 Hennessy Road, Wan Chai, Hong Kong

Tel: (852) 2792 0663 Fax: (852) 2792 7341

Website: http://www.chinapaint.com E-mail: info@chinapaint.com

THE CHINA PAINT MFG. CO., (SHENZHEN) LTD.

Ya Bian Industrial Zone, Huan Zhen Road, Shajing, Baoan, Shenzhen, PRC Postal Code: 518104 Tel: (0755) 3365 8888 Fax: (0755) 3386 9560

Hotline: 400 678 8668 (mobile & land line), 800 830 5712 (land line)



## Giraffe Clear Furniture Lacquer, Gloss #322HK

	-			
	SURFACE PREPARATION			
WOOD SURFACES	Surfaces should be clean, dry and wax-free.			
WOOD SURFACES	Surface should be coated with suitable primer.			
	• Smooth out surface irregularities with Flower Patching Paste #901 and sanding to reach			
IRREGULAR SURFACES	the smoothness requirement.			
	Surface should be coated with suitable primer.			
	COMPLEMENTING PRODUCTS			
WOOD SURFACES	Giraffe General Purpose Lacquer #311HK*			
	* Sales in Hong Kong only			
	2 2 1			
APPLICATION METHOD	APPLICATION  Prush or conventional course			
REDUCTION RATIO	Brush or conventional spray			
BY VOLUME	Reduce 1 part of #311HK with 1.5 parts of #307HK			
REDUCTION/				
CLEANSING SOLVENT	Giraffe Eco Lacquer Reducer #307HK			
OTHER	Stir well before use.			
CONSIDERATIONS	• Moisture content of wood should be $\leq$ 12% for proper curing of the paint.			
$\wedge$	• Do not use nitrocellulose primer for polyurethane painting system.			
/ı\	<ul> <li>Do not mix with other brands' products, or it will cause film failure</li> </ul>			
<u> </u>	• Under humid condition, add 1-5% Giraffe Standard Retarder #414HK to #322HK, in order to			
	prevent film blushing. But this will lenghten the drying time.			
	• Excess film thickness will cause cracking. Maximum 30 microns dry film thickness (d.f.t.) per			
	coat is highly recommended, total d.f.t. should not exceed 200 microns.  • Wash all equipments with solvent promptly after application.			
	• Close the lid tightly after use and store at a cool, dry place (0-35°C)			
HEALTH & SAFETY	• Flashpoint 23°C.			
PRECAUTIONS	<ul> <li>This product is inflammable. Keep away from sparks and open flames.</li> </ul>			
	No smoking should be permitted in the working area.			
	Provide adequate ventilation during paint application.			
	Wear fume masks and protective clothings to avoid skin contact or inhalation of spray mist.      The product covers in contact with the claim week the record by with halo warms weeks and the contact of the conta			
	<ul> <li>If the product comes in contact with the skin, wash thoroughly with luke warm water, and soap or suitable cleanser.</li> </ul>			
	<ul> <li>If the eyes are contaminated, flush with water or diluted boric acid solution for minimum</li> </ul>			
	10 minutes and obtain medical attention at once.			
	Keep out of reach of children.			
	* Type of Regulation Paint under the Air Pollution Control (Volatile Organic Compounds) Regulation of Hong Kong : P10-01			
	VOC content (ready to use) $\leq 550g/L$			

The information given in this sheet is for guidance only and no warranty is provided. Any person using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage arising out of such use.

The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development. It is the user's responsibility to check this sheet is current prior to using the product.





\*A wholly subsidiary of The China Paint Mig. Co. (1992), I.

ISO9001:2008 • Certificate No.:FM34795